

# SheerWeave® Style 7000 BLACKOUT FABRIC

## Specifications

■ Style 7000 is uniquely designed to provide total light blockage when complete room darkening is needed. With a broad range of decorator colors and the look and feel of rich cloth, Style 7000 will enhance the beauty and function of any room.

**Fire Classification:** California U.S. Title 19 (small scale), NFPA 701-2004 TM#1 (small scale), British Standard 5867

**Bacteria and Fungal Resistance:** ASTM G21-96, AATCC 174-1998 Part II and III

**Standard Colors:** White, Birch, Sand, Wheat, Graphite, Onyx, Canyon and Mushroom

**Standard Width:** 94" (238.8cm)

**Standard Roll Length:** 30 Linear Yards (27.4m)

**Composition:** 100% Polyester with Acrylic Foamed Backing (PVC-free)

**Mesh Weight:** 12 oz/yd<sup>2</sup> (407 g/m<sup>2</sup>)

**Fabric Thickness:** .026 in (0.66mm)

**Openness Factor:** Opaque

**Breaking Strength (lb/in):** 205 Warp, 225 Fill

**Elongation to Breaking Point:** 33% Warp, 22% Fill

Colors may vary slightly from swatch samples. All variations are within industry standards.

**Cleaning Instructions:** Fabric should be regularly dusted/vacuumed as appropriate. If commercial spot cleaners are used, they must first be tested and allowed to dry on an inconspicuous area to ensure compatibility.

### Solar Heat Control Properties of Phifer SheerWeave Style 7000 Fabrics Installed Internally, Zero-Degree Profile Angle

Style No.	Color	* Solar Optical Properties				Shading Coefficient w/				
		TS	RS	AS	TV	Single			Insulating	
						1/8CL	1/4CL	1/4HA	1CL	1HA
P62	White	0	64	36	0	0.31	0.31	0.30	0.30	0.24
V40	Onyx	0	64	36	0	0.31	0.31	0.30	0.30	0.24

\* Performance evaluations conducted by Matrix, Inc., Mesa, Arizona.

TS = Solar Transmittance

1/8 CL = 1/8" Clear Glass

1 CL = 1" Insulating Clear Glass

RS = Solar Reflectance

1/4 CL = 1/4" Clear Glass

1HA = 1" Insulating Heat Absorbing Glass

AS = Solar Absorption

1/4HA = 1/4" Heat Absorbing Glass

TV = Visual Transmittance

For complete technical information, current test results, performance specifications and larger samples, contact our Sun Control Marketing Dept.



P. O. BOX 1700 • TUSCALOOSA, ALABAMA 35403-1700 U.S.A.  
PHONE: 205/345-2120 • TOLL FREE 1/800-221-5497  
FAX: 205/391-0799 • www.phifer.com